

VISCOPLEX®

Viscosity Index Improvers (VIIs) for Hydraulic Fluid Applications



Asia Pacific

A RohMax Product



VISCOPLEX® products are polyalkyl methacrylate (PAMA) polymer additives designed to increase the Temperature Operating Window and pump efficiency of formulated hydraulic fluids. VISCOPLEX® VIIs will boost high temperature viscosity and improve low temperature fluidity.

RohMax can help you design a fluid with optimum cost/performance.

Contact your local sales manager to review the complete product line, as well as custom solutions.

Series 7: Viscosity Modifiers for Specialty Hydraulic Fluids

	% VI for ISO 46 ¹	VI ²	PSSI ³	Comments
VISCOPLEX® 7-305	6.1	160	35	For naphthenic aircraft & shock absorber fluids
VISCOPLEX® 7-9xx	NA ⁴	NA ⁴	10-50	VII for phosphate ester fluids

Series 8: Viscosity Modifiers for Industrial Hydraulic Fluids

	% VI for ISO 46 ¹	VI ²	PSSI ³	Comments
VISCOPLEX® 8-100	10.0	150	9	High shear stability
VISCOPLEX® 8-200	8.0	145	19	Good shear stability
VISCOPLEX® 8-350	6.2	160	36	Moderate shear stability
VISCOPLEX® 8-450	5.2	165	51	Balanced performance
VISCOPLEX® 8-702	4.5	165	75	High thickening efficiency
VISCOPLEX® 8-954	4.5	165	75	Dispersant VII

Series 10: Viscosity Modifiers for Biodegradable Hydraulic Fluids

	% VI for ISO 46 ¹	VI ²	PSSI ³	Comments
VISCOPLEX® 10-250	6.1	–	33	Designed for vegetable-derived oils
VISCOPLEX® 10-310	2.9	–	48	VII and CTFI ⁵ with Blue Angel approval
VISCOPLEX® 10-950	4.0	–	80	High thickening efficiency

¹ % treat rate to formulate an ISO 46 high VI fluid based on a 150N oil (30 cSt @ 40 °C, VI = 95)

² Viscosity Index of formulated fluid with the corresponding product and treat rate

³ Permanent shear stability index by ASTM D5621, 40 minute sonic shear

⁴ This type product not suitable for mineral oil formulations

⁵ Cold temperature fluidity improver

This information and all further technical advice is based on our present knowledge and experience. However, they imply no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of the customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

©04/2008 Evonik RohMax Additives GmbH.

VISCOPLEX® and VISCOBASE® are registered trademarks of Evonik RohMax Additives GmbH

Europe, Africa, Mideast:

Evonik RohMax Additives GmbH • Kirschenallee • 64293 Darmstadt • Germany • TEL: +49 6151 1809

Americas:

Evonik RohMax USA, Inc. • 723 Electronic Drive • Horsham, Pennsylvania 19044-2228 • TEL: +1 215 706 5800 • TOLL-FREE: 1 888 876 4629

Asia Pacific:

Evonik RohMax Asia Pacific Pte. Ltd. • 3 International Business Park 07-18 Nordic European Centre • Singapore 609927 • TEL: +65 6899 0080

info-rohmax@evonik.com • www.rohmax.com

